



preliminary p r o d u k t s p e c i f i c a t i o n Koehler Eco 720gsm	rev.:	0
	date	2023-07-25
	sign	Ma

property	unit	tolerance		testing method
		min.	max.	
substance	gsm	710	750	ISO 536
caliper	mikron	900	990	ISO 534
Cobb (60)	gsm		50	ISO 535
abs. humidity	%	5,5	8,5	ISO 20 287
colour difference dL*, da*, db*		-1,5	1,5	DIN 6174

technical changes reserved