



Technické dáta: IQ selection smooth

			80	90	100	120
Plošná hmotnosť	g/m ²	ISO 536	80 ± 3.0	90 ± 3.5	100 ± 4.0	120 ± 4.5
Hrúbka	µm	ISO 534	98 ± 4	106 ± 4	115 ± 4	135 ± 5
Tuhosť L&W	MD mN	ISO 2493-1	110 ± 20	135 ± 20	160 ± 20	270 ± 30
Tuhosť L&W	CD mN	ISO 2493-1	57 ± 13	70 ± 20	80 ± 15	140 ± 20
Hladkosť Bekk	sec	ISO 5627	70 ± 15	70 ± 15	70 ± 15	70 ± 15
Opacita	%	ISO 2471	93.0 ± 1	94.0 ± 1	95.5 ± 1	96.0 ± 1
Belosť s UV	D65 %	ISO 2470	113.5 ± 1.5	113.5 ± 1.5	113.5 ± 1.5	113.5 ± 1.5
CIE Belosť		ISO 11475	170 ± 3.0	170 ± 3.0	170 ± 3.0	170 ± 3.0

Výrobok spĺňa EN 12281, požiadavky na kopírovací papier pre rozmnožovanie suchým tonerom a ISO 9706, požiadavky pre stálosť papiera. Výrobné procesy certifikované podľa ISO 9001, ISO 14001 a OHSAS 18001.

SIGNIFICANCE OF VALUES: 2 SIGMA