

### MUNKEN

### MUNKEN PURE ROUGH

Extraordinary printing demands extraordinary design paper. The uncoated, extra tactile surface of Munken Pure Rough and its creme shade enhance attributes of images and give even more of the natural paper feel. Thanks to high bulk you can choose a lower grammage and keep thickness as well as paper stability for the best final result. Munken Pure Rough is developed for offset print and also suitable for various kinds of printing techniques; flexo, laser, xerography, digital printing, inkjet and for preprint applications. Also available is a crisp white, Munken Polar Rough, and a natural white version, Munken Lynx Rough. Munken Pure Rough standard products are available as FSC<sup>TM</sup> – The mark of responsible forestry. www.fsc.org. FSC-C022692 and PEFC certified.

### MUNKEN

## MUNKEN PURE ROUGH

Grammage (g/m²)	Opacity (%)	Thickness (µm)	Bulk (thickness/grammage)	Whiteness (CIE)	Brightness (ISO 2470/D65 %)	Roughness (Bendtsen, ml/min)
90	90	126	1.4	62	80	550
100	92	140	1.4	62	80	550
120	94	168	1.4	62	80	550
150	96	210	1.4	62	80	550
170	97	238	1.4	62	80	550
300 <sup>B</sup>	100	420	1.4	62	80	550

Screen recommended 133-150 lpi

Values are targets only and can be subject to changes over time without prior notice.

<sup>&</sup>lt;sup>B</sup> Laminated paper

# MUNKEN PURE ROUGH

# **SPECIFICATIONS**

BASIC INFORMATION						
Optimized for Available in Available in colour printing sheets reels						
Uncoated Coated Smooth Rough						
Surface						
Highwhite White Cream						
Shade						
• ENVIRONMENT / SAFETY						
FSC PEFC  PEFCIPS-77-13 Promoting sustainable forest wave path and PEFC  PEFCIPS-77-13 Promoting sustainable forest wave path and Percentage wave path and Percentage variables forest wave path and PeFC  The paper is inspected for Nordic Ecolabelled printing						
Paper Profile Safety of Toys Food contact (ISO 9706)  Age resistant (ISO 9706)  Woodfree						
• PRINTING TECHNIQUES						
TAINTING TECHNICOLS						