

Technical Data Pulse Linen:

	Method		+/-	120 g/m <sup>2</sup>	250 g/m <sup>2</sup>	300 g/m <sup>2</sup>	350 g/m <sup>2</sup>
Basic Weight	ISO 536	g/m <sup>2</sup>	5%	120	250	300	350
Caliper	ISO 534	Micron	10%	140	260	322	375
Bulk	ISO 534	cm <sup>2</sup> /g	-	1.15	1.1	1.07	1.07
CIE Whiteness*	ISO 11475	%	3	167	167	167	167
Opacity	ISO 2471	%	>	94	-	-	-
Moisture Content	ISO 287	%	1	6.5	6.5	6.5	6.5

ECF, ISO 9706 certified, Acid Free, Recyclable, Biodegradable, FSC®-certified

**Printing and finishing recommendations:**

- Printability and runnability: Every method of printing, embossing, punching, creasing, die cutting, laminating and UV varnishing is possible.
- Inks: Good quality semi-fresh inks. The drying process can be slightly accelerated by adding extra desiccant.
- Blankets: For a good graphic impression, use compressible blankets
- Screens: For the offset printing process a screen value of 150 lpi is recommended. For dry offset printing this can be slightly higher, for example 200 lpi. For heavier graphic elements and higher densities, sufficient powder should be applied.
- Drying time: Allow 24 hours drying time after printing.
- Finishing: Prescoring is recommended for board weights and folding against the grain direction.
- Note: To avoid any curling issue, store the paper closed in it's original wrap inside the printing area for at least 24-48 hours. After this conditioning time, the wrapping ca be open and the paper can be utilized.