



# Technický list

Parametry	Standardní	Jednotka	Měření
Gramáž	ISO 536	g/m <sup>2</sup>	80 +/- 2
Tloušťka	ISO 534	µm	109 +/- 3
Volumen	ISO 534		1,36
Obsah vlhkosti	ISO 287	%	4,4 +/- 0,6
Drsnost	ISO 8791	Bendtsen ml/min	230 +/- 50
Bělost	ISO 11475	CIE	167 min.
Jas	ISO 2470-2	%	111 +/- 1
Neprůhlednost	ISO 2471	%	92 min.
Tuhost MD	ISO 2493	m/N	130 +/- 15
Tuhost CD	ISO 2493	m/N	50 +/- 15



References:

Product is made taking into account requirements of DIN EN 12281  
Product made from ECF Pulp

**Sylvamo France SA**

Usine de Saillat

87720 Saillat sur Vienne, France

Extract date: 2024