

Prokladová lepenka

Folding Boxboard

The name of the indicator	Mass 1m² of cardboard, g	Thickness, mm	Humidity, %
Cardboard of the brand of KK	185±15	is not regulated	5,0-12,0 %
	215±15	0,3±0,05	
	250±20	0,4±0,05	
	290±20	0,5±0,06	
	330±20	0,6±0,06	
	350±25	0,7±0,07	
	400±25	0,8±0,07	
Regulatory document of the measurement method	DSTU 2297	DSTU EN 20534	DSTU EN ISO 287

Maximum 450g/m2 ... tloušťka 0,87 mm +/- 0,07 mm

Building Cardboard

The name of the indicator	Norms of indicators for PS brand							
Thickness, mm	0,8±0,1	1,0±0,1	1,25±0,10	1,5±0,10	1,75±0,12	2,00±0,12	2,50±0,13	3,00±0,14
Mass 1m² of cardboard, g	550+40	650+50	945 ± 55	1065±70	1250 ± 80	1400 ± 80	1500±100	1800±100
Humidity, %	9 ±2,0	9 ±2,0	9 ±2,0	9 ±2,0	9 ±2,0	9 ±2,0	9 ±2,0	9 ±2,0